

CIRCOSIL[®] - Guiding Formulation

Mortar for sanitation

(Guiding formulation S 403 MI)

CIRCOSIL 0,5	(1)	12,0	M.-%
CEM I 42,5 R white		20,0	M.-%
Mineral Filler 0 – 90 µm		12,5	M.-%
Trass		2,0	M.-%
Perlite		1,0	M.-%
Sand 0,63 – 1,2 mm		8,0	M.-%
Sand 0,09 – 0,63	ad.	(100	M.-%)
Cellulose ether 15000 mPas		0,07	M.-%
Levellon M 2020	(2)	0,5	M.-%
Sodium-Oleate		0,3	M.-%
Aluminium-Stearate		0,4	M.-%

CIRCOSIL[®] is a registered tradename of CIRKEL

The above data are based on our experience and are given without obligation

Mortar parameters:

Water/Solid ratio	0,310 – 0,315
Mixing acc. EN 1015-2	15 sec. pouring, 75 sec. stirring

Suppliers:

- | | |
|-----------------------------------|---------------------|
| 1) CIRKEL GmbH & Co. KG, D-Rheine | +49(0)5971/96172-11 |
| 2) Mix It GmbH, A-Freistadt | +43(0)7942/77811-0 |

CIRCOSIL[®] is a registered tradename of CIRKEL

The above data are based on our experience and are given without obligation